

520 Eagleton Downs Drive - D Pineville, NC 28134 O: 704.405.2550 F: 704.543.9772 www.americanflamecoat.com

Client: ROYSONS CORPORATION 40 VANDERHOOF AVENUE ROCKAWAY, NJ 07866

Test Report No: 65160-2

Date: 07.05.2018

The sample submitted by the client as: Roysons Corporation – TERRALON/X – Non-Vinyl Wallcovering (ADHERED)

**DATE OF RECEIPT: 06.14.2018** 

**TESTING PERIOD: 14 DAYS** 

TEST REQUESTED: The submitted sample was tested for flammability in Accordance with the procedures outlined in ASTM E-84-98.

**SIGNED** 





520 Eagleton Downs Drive - D Pineville, NC 28134 O: 704.405.2550 F: 704.543.9772 www.americanflamecoat.com

Client: ROYSONS CORPORATION 40 VANDERHOOF AVENUE ROCKAWAY, NJ 07866

Date: 07.05.2018

# **INTRODUCTION:**

This report presents test results of Flame Spread and Smoke Developed Value per ASTM E-84-98. The report also includes Material Identification, Method of Preparation, Mounting and Conditioning of the specimens.

The tests were performed in accordance with the specifications set forth in ASTM E-84-98, Standard Test Method for Surface Burning Characteristics of Building Materials, both as to equipment and test procedures. This test procedure is similar to UL-723, ANSI NO. 2.5, NFPA No. 255 and UBC 42-1.

The test results cover two parameters: Flame Spread and Smoke Developed Values during the 10-minute fire exposure. Inorganic cement board and red oak flooring are used as comparative standards and their responses are assigned arbitrary values of 0 and 100 respectively.

#### PREPARATION AND CONDITIONING:

The test sample identified as Roysons Corporation – TERRALON/X – Non-Vinyl Wallcovering was prepared by adhering the material to 5/8" Type X gypsum board glued using FR - Shur-Stik wallcovering adhesive. This method of sample preparation is described in ASTM E2404-15A, standard practice.

#### **TEST PROCEDURE: Adhered**

The tunnel was thoroughly pre-heated by burning natural gas. When the brick temperature, sensed by a floor thermocouple, had reached the prescribed 105 Fahrenheit +/- 5 Fahrenheit level, the sample was inserted in the tunnel and a test conducted in accordance with the standard ASTM E-84-98 procedures.

The operation of the tunnel was checked by performing a 10-minute test with inorganic board of the day of the test.

This test sample \*meets the A.S.T.M. E-84 Standard
This test sample \*meets the N.F.P.A. LIFE SAFETY CODE 101.



520 Eagleton Downs Drive - D Pineville, NC 28134 O: 704.405.2550 F: 704.543.9772 www.americanflamecoat.com

Client: ROYSONS CORPORATION 40 VANDERHOOF AVENUE ROCKAWAY, NJ 07866

Date: 07.05.2018

## **TEST RESULTS:**

The test results calculated in accordance with ASTM E-84-98 for Flame Spread and Smoke Developed Values are as follows:

Test Specimen: Roysons Corporation – TERRALON/X – Non-Vinyl Wallcovering (ADHERED)

Flame Index = 05 Smoke Developed Value = 90

Observation: Tested Fabric Meets the Requirements for ASTME-84

### Rating: Class A

The National Fire Protection Association Life Safety Code 101, Section 6-5.3, "Interior Wall and Ceiling Finish Classification", has a means of classifying materials with respect to Flame Spread and Smoke Developed when tested in accordance with NFPA 255, "Method of Test of Surface Burning Characteristics of Building Materials", (ASTM E-84)

The classifications are as follows:

Class A Interior Wall & Ceiling Finish:


Flame Spread
Smoke Developed
Class A Interior Wall & Ceiling Finish:

Flame Spread
Flame Spread
0-25


Smoke Developed
0-25

Smoke Developed
0-450

Client: ROYSONS CORPORATION
Report#: 65160-2
Sample: Roysons Corporation – TERRALON/X – Non-Vinyl Wallcovering (ADHERED)



Client: ROYSONS CORPORATION
Report#: 65160-2
Sample: Roysons Corporation – TERRALON/X – Non-Vinyl Wallcovering
(ADHERED)



Client: ROYSONS CORPORATION
Report#: 65160-2
Sample: Roysons Corporation – TERRALON/X – Non-Vinyl Wallcovering (ADHERED)

